VIVID PRODUCT DATA SHEET



-				
Available Sizes				

Up to 20%
Vivid
Colour, Made in the UK
Select Collection
VVDIA
White
Gloss
Internal Only
-
-
Glazed Ceramic
BIII
86.00
VI

Samples Service

400x150x10mm

Tel: +44 (0) | 782 524 043 Fax: +44 (0) | 782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Physical Properties				
Test / Standard		Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.5%≤ ± 2mm	±0.25%	
-]+	Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	± 0.15%	
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.4%	
\downarrow	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.2%	
$\left \begin{array}{c} \longrightarrow \\ \longleftarrow \end{array} \right $	Warpage EN ISO 10545-2	±0.5%≤ ± 2mm	0.30%	
	Water Absorption EN ISO 10545-3	10% to 20%	15% to 17%	
	Modulus of Rupture EN ISO 10545-4	Ave I5N/mm²	25N/mm²	
<u>*</u>	Frost Resistance Not Applicable	N/A	Not suitable	
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A-B (better)	
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 3 (better)	
[\vec{\pi}]	Crazing Resistance EN ISO 10545-11	Pass	Pass	
	UV Colour Resistance		Unaffected by light	
	Scratch Hardness BS6431:Part13/EN101	≥3	4	
	Fire Rating		Class A I Non Combustible	
kg	Weight/m² Thickness: I 0mm		17kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/201). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshire, SK9 IBU. Registed in England No. 566694. Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks of H&R Johnson Tiles. Elmited and licensed to Norcros Group (Holdings) Limited trading as Johnson Tiles. © 2021 Johnson Tiles. All rights reserved.

