

## Absolute Collection – Mode Sable Bush Hammered



## Available Sizes

## Tile

600 x 100 x 11 mm  
 600 x 150 x 11 mm  
 600 x 200 x 11 mm  
 600 x 300 x 11 mm  
 600 x 600 x 11 mm

Descriptive Colour	Sable
Finish	Bush Hammered
Range	Mode
Shortcode	MOD02B
Suitabilities	<input type="checkbox"/> Internal & External <input type="checkbox"/> Internal & External
Material	All Porcelain
Classification	B I a
Light Reflectance Value	40.00
NCS	30 I 0-Y20R
Colour Shade Variation (CSV)	V2
Pendulum Dry 4S	36+
Pendulum Wet 4S	36+
TRL Wet Barefoot	36+
Rz Value (Surface Microroughness)	34.4
R Value (DIN51130)	R I I
Wet Ramp (DIN51097)	C
Traffic	Commercial

## Physical properties

Test	Standard	Requirement	Typical test value
Length/Width	EN ISO 10545-2	$\pm 0.6\% \leq \pm 2\text{mm}$	Pass
Thickness	EN ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	$\pm 5\%$
Straightness of Sides	EN ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	$\pm 0.3\%$
Rectangularity	EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	$\pm 0.4\%$
Surface Flatness	EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	$\pm 0.3\%$
Water Absorption	EN ISO 10545-3	$\leq 0.5\%$	$< 0.1\%$
Modulus of Rupture	EN ISO 10545-4	$\geq 35\text{N/mm}^2$	$35\text{N/mm}^2$
Abrasion Resistance	EN ISO 10545-6	$\leq 175\text{mm}^3$	$\leq 175\text{mm}^3$
Thermal Shock	EN ISO 10545-9	Pass	Pass
Frost Resistance	EN ISO 10545-12	Resistant	Resistant
Chemical Resistance	EN ISO 10545-13	Min Class B	Class A-B (better)
Stain Resistance	EN ISO 10545-14	Min Class 3	Class 5
Fire Rating			Class A IFL Non Combustible
Weight/m <sup>2</sup>			
Thickness: 10.5mm			23kg 25kg
Thickness: 11mm			

## Samples

Tel: +44 (0) 1782 524043  
 Fax: +44 (0) 1782 577379  
 Email: [samples@johnson-tiles.com](mailto:samples@johnson-tiles.com)

## Technical helpline

Tel: +44 (0) 1782 524111  
 Fax: +44 (0) 1782 577379  
 Email: [techadvice@johnson-tiles.com](mailto:techadvice@johnson-tiles.com)

[www.johnson-tiles.com](http://www.johnson-tiles.com)

The colours shown on the tile products in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are correct at the time of testing and represent the standard production value. Please note: Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The Pendulum test results have been displayed in line with the Health and Safety Executive guidelines whereby 0-24 represents a high slip potential, 25-35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures accurate at time of data sheet creation (23/09/2019). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshire, SK9 1BU. Registered in England number 566694. Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and the product names are the trademarks of H&R Johnson Tiles Limited and licensed to Norcros Group (Holdings) Limited, trading as Johnson Tiles. ©2013 Johnson Tiles. All rights reserved.