## **BELLAGIO** PRODUCT DATA SHEET



	Range	Bellagio
	Category	Stone, Speckle, Floor Tiles
A.	Collection	Absolute Collection
31.	Short Code	BLG03N
ele -	Colour	Grey
and a state of the	Finish	Natural
a de la	Wall Suitability	Internal & External
9.6	Floor Suitability	Internal Only
	Wet Barefoot	-
	Material	Glazed Porcelain
	Classificiation	Bla
	Light Reflectance Value	32.00
	CSV	V2
	PTV (96)	Wet 25-35 Dry 36+
	PTV (55)	-
	R Value	9
	Wet Ramp	-
	PEI	ш
	Traffic	Light Commercial

Up to 60%

Physical Properties			
Test / Standard	Requirement	Test Result	
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass	
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
↓ Surface Flatness   ↑ ↑ EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
Water Absorption EN ISO 10545-3	≤0.5%	Pass	
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass	
Frost Resistance EN ISO 10545-12	Resistant	Resistant	
Chemical Resistance EN ISO 10545-13	Min Class B	Class A	
Stain Resistance EN ISO 10545-14	Min Class 3	Min Class 3	
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg Weight/m <sup>2</sup> Thickness:10mm		21.53kg	

## Samples Service

Available Sizes

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

## Technical Helpline

Tel: +44 (0)1782 524 111 Fax: +44 (0)1782 577 379 Email: techadvice@johnson-tiles.com

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (17/05/2023). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

