

# BLAKE PRODUCT DATA SHEET



## Available Sizes

330x330x7.2mm  
600x300x7.8mm

## Samples Service

Tel: +44 (0)1782 524 043  
Fax: +44 (0)1782 577 379  
Email: [samples@johnson-tiles.com](mailto:samples@johnson-tiles.com)

## Technical Helpline









Tel: +44 (0)1782 524 111  
Fax: +44 (0)1782 577 379  
Email: [techadvice@johnson-tiles.com](mailto:techadvice@johnson-tiles.com)

[www.johnson-tiles.com](http://www.johnson-tiles.com)

 Recycled Content Up to 10%

Range	Blake
Category	Stone, Floor Tiles, PTV 36+ Tiles
Collection	Select Collection
Short Code	BLK03M
Colour	Taupe
Finish	Matt
Wall Suitability	Internal & External
Floor Suitability	Internal Only
Wet Barefoot	-
Material	Glazed Porcelain
Classification	Bla
Light Reflectance Value	40.00
CSV	V4
PTV (96)	Wet 36+ Dry 36+
PTV (55)	-
R Value	10
Wet Ramp	B
PEI	IV
Traffic	Commercial

## Physical Properties

Test / Standard	Requirement	Test Result
 <b>Length/Width</b> EN ISO 10545-2	$\pm 0.6\% \leq \pm 2\text{mm}$	Pass
 <b>Thickness</b> EN ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	Pass
 <b>Straightness of Sides</b> EN ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	Pass
 <b>Rectangularity</b> EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass
 <b>Surface Flatness</b> EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass
 <b>Water Absorption</b> EN ISO 10545-3	$\leq 0.5\%$	Pass
 <b>Modulus of Rupture</b> EN ISO 10545-4	$\geq 35\text{N/mm}^2$	Pass
 <b>Thermal Shock</b> EN ISO 10545-9	Pass	Pass
 <b>Frost Resistance</b> EN ISO 10545-12	Resistant	Resistant
 <b>Chemical Resistance</b> EN ISO 10545-13	Min Class B	Pass
 <b>Stain Resistance</b> EN ISO 10545-14	Min Class 3	Pass
 <b>Fire Rating</b> Not Applicable	N/A	Class A I FL Non Combustible
 <b>Weight/m²</b> Thickness: 6mm Thickness: 7.2mm Thickness: 7.8mm Thickness: 8.3mm		12.3kg 15.8kg 17.25kg 16.89kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (30/04/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

Est. 1901  
**JOHNSON**  
TILES