

# BOUNDARY PRODUCT DATA SHEET



## Available Sizes

600x600x20mm

## Samples Service

Tel: +44 (0)1782 524 043

Fax: +44 (0)1782 577 379

Email: [samples@johnson-tiles.com](mailto:samples@johnson-tiles.com)

## Technical Helpline

Tel: +44 (0)1782 524 111

Fax: +44 (0)1782 577 379

Email: [techadvice@johnson-tiles.com](mailto:techadvice@johnson-tiles.com)

[www.johnson-tiles.com](http://www.johnson-tiles.com)

 Recycled Content Up to 10%

|                         |                                    |
|-------------------------|------------------------------------|
| Range                   | <b>Boundary</b>                    |
| Category                | <b>Stone, Floor Tiles, PTV 36+</b> |
|                         | <b>Tiles, 2cm</b>                  |
| Collection              | <b>Select Collection</b>           |
| Short Code              | <b>BON04E</b>                      |
| Colour                  | <b>Castlerock</b>                  |
| Finish                  | <b>Natural+ 2cm</b>                |
| Wall Suitability        | <b>Internal &amp; External</b>     |
| Floor Suitability       | <b>Internal &amp; External</b>     |
| Wet Barefoot            | <b>Yes</b>                         |
| Material                | <b>Glazed Porcelain</b>            |
| Classification          | <b>Bla</b>                         |
| Light Reflectance Value | <b>24.00</b>                       |
| CSV                     | <b>V2</b>                          |
| PTV (96)                | <b>Wet 36+ Dry 36+</b>             |
| PTV (55)                | <b>Wet 36+</b>                     |
| R Value                 | <b>11</b>                          |
| Wet Ramp                | <b>-</b>                           |
| PEI                     | <b>IV</b>                          |
| Traffic                 | <b>Commercial</b>                  |

## Physical Properties

| Test / Standard                                                                                                                    | Requirement                       | Test Result                                |
|------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------|--------------------------------------------|
|  <b>Length/Width</b><br>EN ISO 10545-2          | $\pm 0.6\% \leq \pm 2\text{mm}$   | <b>Pass</b>                                |
|  <b>Thickness</b><br>EN ISO 10545-2             | $\pm 5\% \leq \pm 0.5\text{mm}$   | <b>Pass</b>                                |
|  <b>Straightness of Sides</b><br>EN ISO 10545-2 | $\pm 0.5\% \leq \pm 1.5\text{mm}$ | <b>&lt; 0.2%</b>                           |
|  <b>Rectangularity</b><br>EN ISO 10545-2        | $\pm 0.6\% \leq \pm 2\text{mm}$   | <b><math>\pm 0.2\%</math></b>              |
|  <b>Surface Flatness</b><br>EN ISO 10545-2      | $\pm 0.5\% \leq \pm 2\text{mm}$   | <b>Pass</b>                                |
|  <b>Water Absorption</b><br>EN ISO 10545-3      | $\leq 0.5\%$                      | <b>&lt; 0.1%</b>                           |
|  <b>Modulus of Rupture</b><br>EN ISO 10545-4    | $\geq 1300\text{N/mm}^2$          | <b><math>\geq 1300\text{N/mm}^2</math></b> |
|  <b>Thermal Shock</b><br>EN ISO 10545-9         | Pass                              | <b>Pass</b>                                |
|  <b>Frost Resistance</b><br>EN ISO 10545-12     | Resistant                         | <b>Resistant</b>                           |
|  <b>Chemical Resistance</b><br>EN ISO 10545-13  | Min Class B                       | <b>Class A</b>                             |
|  <b>Stain Resistance</b><br>EN ISO 10545-14   | Min Class 3                       | <b>Class 5</b>                             |
|  <b>Fire Rating</b><br>Not Applicable         | N/A                               | <b>Class A I FL Non Combustible</b>        |
|  <b>Weight/m²</b><br>Thickness 20mm           |                                   | <b>46.31 kg</b>                            |

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

Est. 1901  
**JOHNSON  
TILES**