

# BOUNDARY PRODUCT DATA SHEET



## Available Sizes

600x600x9mm

## Samples Service

Tel: +44 (0)1782 524 043

Fax: +44 (0)1782 577 379

Email: [samples@johnson-tiles.com](mailto:samples@johnson-tiles.com)

## Technical Helpline

Tel: +44 (0)1782 524 111

Fax: +44 (0)1782 577 379













Email: [techadvice@johnson-tiles.com](mailto:techadvice@johnson-tiles.com)

[www.johnson-tiles.com](http://www.johnson-tiles.com)

 Recycled Content Up to 10%

Range	Boundary
Category	Stone, Floor Tiles
Collection	Select Collection
Short Code	BON05L
Colour	Storm
Finish	Lapato
Wall Suitability	Internal & External
Floor Suitability	Internal Only
Wet Barefoot	-
Material	Glazed Porcelain
Classification	Bla
Light Reflectance Value	11.00
CSV	V2
PTV (96)	Wet 0-24 Dry 36+
PTV (55)	-
R Value	-
Wet Ramp	-
PEI	III
Traffic	Light Commercial

## Physical Properties

Test / Standard	Requirement	Test Result
 <b>Length/Width</b> EN ISO 10545-2	$\pm 0.6\% \leq \pm 2\text{mm}$	Pass
 <b>Thickness</b> EN ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	Pass
 <b>Straightness of Sides</b> EN ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	< 0.2%
 <b>Rectangularity</b> EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	< 0.2%
 <b>Surface Flatness</b> EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	< 0.2%
 <b>Water Absorption</b> EN ISO 10545-3	$\leq 0.5\%$	< 0.1%
 <b>Thermal Shock</b> EN ISO 10545-9	Pass	Pass
 <b>Frost Resistance</b> EN ISO 10545-12	Resistant	Resistant
 <b>Chemical Resistance</b> EN ISO 10545-13	Min Class B	Class A
 <b>Stain Resistance</b> EN ISO 10545-14	Min Class 3	Class 5
 <b>Fire Rating</b> Not Applicable	N/A	Class A1 FL Non Combustible
 <b>Weight/m²</b> Thickness: 9mm Thickness: 20mm		19.5kg 46.31kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

Est. 1901  
**JOHNSON  
TILES**