

BUCKINGHAM WALL PRODUCT DATA SHEET



Available Sizes

900x300x11mm

Samples Service

Tel: +44 (0)1782 524 043

Fax: +44 (0)1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0)1782 524 111

Fax: +44 (0)1782 577 379













Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

 Recycled Content

Up to 30%

Range	Buckingham Wall
Category	Marble, Structure
Collection	Absolute Collection
Short Code	BUCK2W
Colour	Light Grey
Finish	Natural - Wiggle Structure
Wall Suitability	Internal Only
Floor Suitability	-
Wet Barefoot	-
Material	Glazed Ceramic
Classification	BIII
Light Reflectance Value	55.00
CSV	V2

Physical Properties		
Test / Standard	Requirement	Test Result
 Length/Width EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass
 Thickness EN ISO 10545-2	$\pm 10\% \leq \pm 0.5\text{mm}$	Pass
 Straightness of Sides EN ISO 10545-2	$\pm 0.3\% \leq \pm 1.5\text{mm}$	Pass
 Rectangularity EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass
 Surface Flatness EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass
 Water Absorption EN ISO 10545-3	10% to 20%	Pass
 Modulus of Rupture EN ISO 10545-4	Ave 15N/mm ²	$\geq 15\text{N/mm}^2$
 Frost Resistance Not Applicable	N/A	Not suitable
 Chemical Resistance EN ISO 10545-13	Min Class B	Class A
 Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
 Fire Rating		Class A1 Non Combustible
 Weight/m² Thickness 11mm		18.5kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

Est. 1901
JOHNSON
TILES