
BUCKINGHAM PRODUCT DATA SHEET





Available Sizes

300x300x9mm (50x50mm)

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Recycled Content	Up to 30%	
Pango	Puskingham	
Range	Buckingham	
Category	Marble, Mosaic, Floor Tiles,	
	PTV 36+ Tiles	
Collection	Absolute Collection	
Short Code	BUC4GM	
Colour	Anthracite	
Finish	Grip - 50mm Square	
	Mosaic	
Wall Suitability	Internal & External	
Floor Suitability	Internal & External	
Wet Barefoot	Yes	
Material	Porcelain	
Classificiation	Bla	
Light Reflectance Value	15.00	
CSV	V2	
PTV (96)	Wet 36+ Dry 36+	
PTV (55)	Wet 36+	
R Value	11	
Wet Ramp	С	
PEI	-	
Traffic	Commercial	

Physical Properties			
Test / Standard		Requirement	Test Result
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
→	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
-]+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥55N/mm²
	Abrasion Resistance EN ISO 10545-6	≤175mm³	<109mm³
	Thermal Shock EN ISO 10545-9	Pass	Pass
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg	Weight/m² Thickness: 9mm		21kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 − 24 represents a high slip potential, 25 − 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (11/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

