## **BUCKINGHAM** PRODUCT DATA SHEET



	Category	Marble, Mosaic, Floor Tiles
	Collection	Absolute Collection
	Short Code	BUC2BM
11	Colour	Light Grey
	Finish	Soft Bush Hammered -
		50mm Square Mosaic
	Wall Suitability	Internal & External
	Floor Suitability	Internal Only
Available Sizes	Wet Barefoot	-
300x300x9mm (50x50mm)	Material	Porcelain
	Classificiation	Bla
	Light Reflectance Value	55.00
	CSV	V2
	PTV (96)	Wet 25-35 Dry 36+
Samples Service	PTV (55)	-
Tel: +44 (0) I 782 524 043 Fax: +44 (0) I 782 577 379	R Value	9
Email: samples@johnson-tiles.com	Wet Ramp	Α
Technical Helpline Tel: +44 (0) 1782 524	PEI	-
Fet: +44 (0)1782 524 111 Fax: +44 (0)1782 577 379 Email: techadvice@johnson-tiles.com	Traffic	Commercial

 $\varnothing$  Recycled Content

Range

Up to 30%

Buckingham

Physical Properties		
Test / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
→ Thickness ← EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
◆ ↑ ◆ Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥55N/mm²
Abrasion Resistance EN ISO 10545-6	≤175mm³	<109mm <sup>3</sup>
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Class A
Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg Weight/m <sup>2</sup>		21kg

## Email: samples

## Technical Heli

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (11/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.



