CHROMA PRODUCT DATA SHEET



${\cal O}$ Recycled Content	Up to 20%
Range	Chroma
Category	Colour
Collection	Select Collection
Short Code	CHG22A
Colour	Coffee
Finish	Gloss
Wall Suitability	Internal Only
Floor Suitability	-
Wet Barefoot	-
Material	Glazed Ceramic
Classificiation	BIII
Light Reflectance Value	24.00
CSV	VI

Physical Properties Test / Standard Requirement Test Result Length/Width ±0.5%≤ ± 2mm Pass EN ISO 10545-2 Straightness of Sides ±0.3% ≤ ± 1.5mm Pass EN ISO 10545-2 Rectangularity _____+ $\pm 0.5\% \leq \pm 2mm$ Pass EN ISO 10545-2 $\stackrel{\checkmark}{\overleftarrow{}}$ Surface Flatness $\pm 0.5\% \leq \pm 2mm$ Pass EN ISO 10545-2 Warpage ±0.5%≤ ± 2mm Pass \vdash EN ISO 10545-2 Water Absorption 10% to 20% Pass EN ISO 10545-3 **Modulus of Rupture** Ĉ Ave 15N/mm² Pass EN ISO 10545-4 Frost Resistance 淋 N/A Not suitable Not Applicable **Chemical Resistance** Æ Min Class B Pass EN ISO 10545-13 Stain Resistance Min Class 3 Pass EN ISO 10545-14 **Crazing Resistance** Pass Pass EN ISO 10545-11 **UV Colour Resistance** Unaffected by light

Available Sizes 300x100x8mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0)1782 524 111 Fax: +44 (0)1782 577 379 Email: techadvice@johnson-tiles.com Class A1 Non

B Fire Rating Combustible Weight/m² kg Thickness: 8mm 14.1kg

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be analy variations in sip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to as all variations in the slip resistance of the slip resent is allow of the slip resent as a slip of the slip resent as a slip of the slip resent of the slip resent as a slip slip potential. Z5 – 35 slip leads an odders to slip potentia and 36+ represents a low slip potential. All rights reserved.

JOHNSON

