CHROMA PRODUCT DATA SHEET



Ø Recycled Content	Up to 20%		
Range	Chroma		
Category	Colour		
Collection	Select Collection		
Short Code	CHS27A		
Colour	Graphite		
Finish	Satin		
Wall Suitability	Internal Only		
Floor Suitability	-		
Wet Barefoot	-		
Material	Glazed Ceramic		
Classificiation	BIII		
Light Reflectance Value	8.00		
CSV	VI		

Physi	Physical Properties				
Test /	Standard	Requirement	Test Result		
	Length/Width EN ISO 10545-2	±0.5%≤ ± 2mm	Pass		
 +	Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	Pass		
 -	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass		
 ${\underset{\displaystyle \leftarrow}{=}}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass		
 ${\underset{\downarrow}{\overset{\downarrow}{}}}$	Warpage EN ISO 10545-2	±0.5%≤ ± 2mm	Pass		
	Water Absorption EN ISO 10545-3	10% to 20%	Pass		
	Modulus of Rupture EN ISO 10545-4	Ave 15N/mm²	Pass		
 *	Frost Resistance Not Applicable	N/A	Not suitable		
 ð	Chemical Resistance EN ISO 10545-13	Min Class B	Pass		
	Stain Resistance EN ISO 10545-14	Min Class 3	Pass		
X	Crazing Resistance EN ISO 10545-11	Pass	Pass		
	UV Colour Resistance		Unaffected by light		

Available Sizes 300x100x8mm

Samples Service

Tel: +44 (0)1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0)1782 524 111 Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com

Class A1 Non Fire Rating

Combustible Weight/m² kg Thickness: 8mm 14.1kg

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 – 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36 represents a low slip potential. All figures are accurate at the time of this data sheets creation (16/06/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Englan No. 15600432. © 2025 Johnson Tiles. All rights reserved.

JOHNSON _____TILES

