
# **CHROMA** PRODUCT DATA SHEET



${\cal O}$ Recycled Content	Up to 20%	
Range	Chroma	
Category	Colour	
Collection	Select Collection	
Short Code	CHGIIA	
Colour	Sand	
Finish	Gloss	
Wall Suitability	Internal Only	
Floor Suitability	-	
Wet Barefoot	-	
Material	Glazed Ceramic	
Classificiation	BIII	
Light Reflectance Value	71.00	
CSV	VI	

Physical Properties				
Test	/ Standard	Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.5%≤ ± 2mm	Pass	
+	Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	Pass	
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
$\stackrel{\checkmark}{}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
$\stackrel{\rightarrow}{\underset{\leftarrow}{\longrightarrow}}$	<b>Warpage</b> EN ISO 10545-2	±0.5%≤ ± 2mm	Pass	
	Water Absorption EN ISO 10545-3	10% to 20%	Pass	
	<b>Modulus of Rupture</b> EN ISO 10545-4	Ave 15N/mm²	Pass	
*	<b>Frost Resistance</b> Not Applicable	N/A	Not suitable	
Æ	Chemical Resistance EN ISO 10545-13	Min Class B	Pass	
	Stain Resistance EN ISO 10545-14	Min Class 3	Pass	
X	Crazing Resistance EN ISO 10545-11	Pass	Pass	
	UV Colour Resistance		Unaffected by light	
	Fire Rating		Class A1 Non Combustible	

## **Available Sizes** 300x100x8mm

#### Samples Service

Tel: +44 (0)1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

#### Technical Helpline

Tel: +44 (0)1782 524 111 Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com

Weight/m<sup>2</sup> kg 14.1kg Thickness: 8mm

### www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.



