COAST PRODUCT DATA SHEET



			Test / Standard	Requ
				Kequ
	Range	Coast	Length/Width EN ISO 10545-2	±0.6%
and the second states of the	Category	Stone, Speckle, Floor Tiles,		
	· ·	PTV 36+ Tiles	Thickness EN ISO 10545-2	±5%≤
	Collection	Select Collection	Straightness of Sides	±0.5%
	Short Code	CST02N	EN ISO 10545-2	
	Colour	Beige	EN ISO 10545-2	±0.5%
	Finish	Natural	Surface Flatness EN ISO 10545-2	±0.59
	Wall Suitability	Internal & External	Water Absorption	≤0.5%
	Floor Suitability	Internal Only	EN ISO 10545-3	
Available Sizes	Wet Barefoot	-	Modulus of Rupture EN ISO 10545-4	≥35N
600x600x10.5mm 1190x600x10.5mm	Material	Un-glazed Porcelain	Thermal Shock EN ISO 10545-9	Pass
890x890x10.5mm 600x300x10.5mm	Classificiation	Bla		
	Light Reflectance Value	53.00	Frost Resistance EN ISO 10545-12	Resis
	CSV	V4	Chemical Resistance EN ISO 10545-13	Min 0
	PTV (96)	Wet 36+ Dry 36+	Stain Resistance EN ISO 10545-14	
Samples Service	PTV (55)	-		
Tel: +44 (0) 782 524 043 Fax: +44 (0) 782 577 379	R Value	10	UV Colour Resistance	
Email: samples@johnson-tiles.com	Wet Ramp	В	Fire Rating Not Applicable	N/A
Technical Helpline Tel: +44 (0)1782 524 111	PEI	-	kg Weight/m ²	
Fax: +44 (0) 1782 577 379	Traffic	Commercial	Thickness: 10.5mm	
Email: techadvice@johnson-tiles.com				

Up to 10%

Physical Properties auirement Test Result 6%≤ ± 2mm ±0.3% %≤ ± 0.5mm ±3% 5% ≤ ± 1.5mm ±0.3% 5% ≤ ± 2mm ±0.3% 5% ≤ ± 2mm ±0.3% 5% ≤**0**.1% 5N/mm² ≥45N/mm² Pass Resistant sistant Class B Class A Class 5 Unaffected by light Class A I FL Non Combustible 24.35kg

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. 25 - 35 signifies a moderate slip potentia and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (30/04/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST& 5JZ. Registered in Engl

 \varnothing Recycled Content

