COLOURS & FITTINGS PRODUCT DATA SHEET





Available Sizes

150x150x8mm 150x75x8mm

${oldsymbol arOmega}$ Recycled Content	Up to 20%	
Range	Colours & Fittings	
Category		
Collection	Minton Hollins Collection	
Short Code	MH2B	
Colour	China Blue	
Finish	Gloss	
Wall Suitability	Internal Only	
Floor Suitability	-	
Wet Barefoot	-	
Material	Glazed Ceramic	
Classificiation	BIII	
CSV	VI	

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Physical Properties			
Test /	Standard	Requirement	Test Result
	Length/Width EN ISO 10545-4	±0.5%≤ ± 2mm	±0.25%
	Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	± 0.15%
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	± 0.4%
\downarrow	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.2%
$\stackrel{\longrightarrow}{\sqsubseteq}$	Warpage EN ISO 10545-2	±0.5%≤ ± 2mm	0.30%
	Water Absorption EN ISO 10545-3	I 0% to 20%	15% to 17%
	Modulus of Rupture EN ISO 10545-4	Ave I5N/mm²	25N/mm²
※	Frost Resistance Not Applicable	N/A	Not suitable
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A-B (better)
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 3 (better)
[\mathred{\matred{\matro	Crazing Resistance EN ISO 10545-11	Pass	Pass
~~~ ~~~ ~~~~	UV Colour Resistance		Unaffected by light
	Scratch Hardness BS6431:Part13/EN101	≥3	4
	Fire Rating		Class A I Non Combustible

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 51/2. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

