CONCRETO PRODUCT DATA SHEET



www.johnson-tiles.com

	Short Code	CCR01G
	Colour	Bone
	Finish	Grip
	Wall Suitability	Internal & External
	Floor Suitability	Internal & External
Available Sizes 605x305x7.8mm	Wet Barefoot	Yes
	Material	Glazed Porcelain
	Classificiation	Bla
	Light Reflectance Value	55.00
	CSV	V4
	PTV (4S)	Wet 36+ Dry 36+
Samples Service	PTV (TRL)	Wet 36+
Tel: +44 (0)1782 524 043 Fax: +44 (0)1782 577 379	R Value	12
Email: samples@johnson-tiles.com	Wet Ramp	c
Technical Helpline Tel: +44 (0)1782 524 111	PEI	IV
Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com	Traffic	Commercial
Email: teenaamee@jonnbon=tites.com		

 \mathcal{O} Recycled Content

Range Category

Collection

Up to 10%

Concreto

36+ Tiles

Concrete, Floor Tiles, PTV

Absolute Collection

Physical Properties				
Test /	Standard	Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
$\stackrel{\flat}{=}$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass	
+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
$\stackrel{\checkmark}{\underset{\land \land}{}}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
	Water Absorption EN ISO 10545-3	≤0.5%	Pass	
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass	
	Thermal Shock EN ISO 10545-9	Pass	Pass	
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant	
B	Chemical Resistance EN ISO 10545-13	Min Class B	Class A	
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5	
242 242 242 242 242 242 242 242 242 242	UV Colour Resistance		Unaffected by light	
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg	Weight/m ² Thickness: 7.2mm Thickness: 7.8mm Thickness: 8mm Thickness: 9.5mm Thickness: 10mm		15.78kg 16.9kg 18.39kg 21.03kg 22.24kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduit the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a line high slip potential, 25 - 35 signifies a moderate slip par and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/2021). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station I Wilmslow, Cheshire, SK9 I BU. Registed in England In 10e, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks Johnson Tiles. © 2021 Johnson Tiles. All rights reserved.

