
CONCRETO PRODUCT DATA SHEET



Available Sizes

300x300x8mm (50x44mm)

Samples Service

Tel: +44 (0) | 782 524 043 Fax: +44 (0) | 782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

$oldsymbol{arrho}$ Recycled Content	Up to 10%	
Range	Concreto	
Category	Concrete, Mosaic, Floor	
	Tiles, PTV 36+ Tiles	
Collection	Absolute Collection	
Short Code	CCR4NM	
Colour	Charcoal	
Finish	Natural - Weave Mosaic	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	12.00	
CSV	V4	
PTV (4S)	Wet 36+ Dry 36+	
PTV (TRL)	-	
R Value	10	
Wet Ramp	A	
PEI	II	
Traffic	-	

Physical Properties			
Test	Test / Standard Requirement		Test Result
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
]+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
$\begin{array}{ c c }\hline \downarrow \\\hline \uparrow \uparrow \\\hline \end{array}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	≤0.5%	Pass
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass
	Thermal Shock EN ISO 10545-9	Pass	Pass
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
\$\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\	UV Colour Resistance		Unaffected by light
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg	Weight/m² Thickness: 7.2mm Thickness: 7.8mm Thickness: 8mm Thickness: 9.5mm Thickness: 10mm		15.78kg 16.9kg 18.39kg 21.03kg 22.24kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a lips slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/201). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshine, SK9 IBU. Registed in England No. 566694. Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks of H&R Johnson Tiles Limited and licensed to Norcros Group (Holdings) Limited trading as Johnson Tiles. © 2021 Johnson Tiles. All rights reserved.

