CONTEMPO PRODUCT DATA SHEET



Available Sizes 600x600x8.3mm 1200x600x9.2mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

arrho Recycled Content	Up to 10%	
Range	Contempo	
Category	Stone, Marble, Floor Tiles,	
	PTV 36+ Tiles	
Collection	Select Collection	
Short Code	СОТ03G	
Colour	Armani - Platinum	
Finish	Grip	
Wall Suitability	Internal & External	
Floor Suitability	Internal & External	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	50.00	
CSV	V2	
PTV (96)	Wet 36+ Dry 36+	
PTV (55)	-	
R Value	10	
Wet Ramp	-	
PEI	IV	
Traffic	Commercial	

Physical Properties			
Test / Standard		Requirement	Test Result
$ \bigcirc $	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
$\begin{array}{ c c }\hline \downarrow \\ \hline \uparrow \\ \end{array}$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
]+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
$\boxed{ \begin{array}{c} \downarrow \\ \uparrow \uparrow \uparrow \end{array} }$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass
	Thermal Shock EN ISO 10545-9	Pass	Pass
<u>*</u>	Frost Resistance EN ISO 10545-12	Resistant	Resistant
	Chemical Resistance EN ISO 10545-13	Min Class B	Pass
	Stain Resistance EN ISO 10545-14	Min Class 3	Pass
~~~~ ~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~	UV Colour Resistance		Unaffected by light
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg	Weight/m ² Thickness: 8.3mm Thickness: 8.4mm Thickness: 9.2mm		19.1kg 20kg 20.5kg

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in stip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (19/05/2023). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Englan No. 15600432. © 2025 Johnson Tiles. All rights reserved.

