CONTOUR PRODUCT DATA SHEET

${\cal O}$ Recycled Content	Up to 80%
Range	Contour
Category	Colour, Structure
Collection	Absolute Collection
Short Code	CNT01D
Colour	White
Finish	Gloss - 3D Strips
Wall Suitability	Internal Only
Floor Suitability	-
Wet Barefoot	-
Material	Glazed Ceramic
Classificiation	BIII
Light Reflectance Value	90.00
CSV	VI
	Range Category Collection Short Code Colour Finish Wall Suitability Floor Suitability Wet Barefoot Material Classificiation Light Reflectance Value

Length/Width ±0.5%≤ ± 2mm EN ISO 10545-2 Thickness ±10%≤±0.5mm EN ISO 10545-2 Straightness of Sides ±0.3% ≤ ± 1.5mm EN ISO 10545-2 Rectangularity _____+ $\pm 0.5\% \leq \pm 2mm$ EN ISO 10545-2 Surface Flatness ±0.5% ≤ ± 2mm $\uparrow \uparrow$ EN ISO 10545-2 Water Absorption 10% to 20% EN ISO 10545-3 **Modulus of Rupture** Ave 15N/mm² EN ISO 10545-4 Thermal Shock ×1 Pass EN ISO 10545-9 Frost Resistance × N/A Not Applicable

Physical Properties

Available Sizes 300x75x15.5mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0)1782 524 111 Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be analy variations in tip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to as all variations in the slip resistance of the slip resent is allow of the slip resent as a slip of the slip resent as a slip of the slip resent of the slip resent as a slip slip potential. Z5 – 35 slip leads an odderate slip potentia and 36+ represents a low slip potential. All rights reserved.





