CORTONA PRODUCT DATA SHEET



	Category	Stone, Mosaic, Floor Tiles,
and the second sec		PTV 36+ Tiles
	Collection	Absolute Collection
	Short Code	COR03G
	Colour	Grey
	Finish	Grip - Square Mosaic
	Wall Suitability	Internal & External
	Floor Suitability	Internal & External
Available Sizes	Wet Barefoot	Yes
300x300x6mm (100x100mm)	Material	Glazed Porcelain
	Classificiation	Bla
	Light Reflectance Value	38.00
	CSV	V4
	PTV (96)	Wet 36+ Dry 36+
Samples Service	PTV (55)	Wet 36+
Tel: +44 (0)1782 524 043 Fax: +44 (0)1782 577 379	R Value	12
Email: samples@johnson-tiles.com	Wet Ramp	с
Technical Helpline Tel: +44 (0)1782 524 111	PEI	IV
Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com	Traffic	Commercial

Range

Up to 10%

Cortona

est / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
	±5%≤ ± 0.5mm	Pass
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
↓ Surface Flatness ↑ ↑ EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Pass
Stain Resistance EN ISO 10545-14	Min Class 3	Pass
UV Colour Resistance		Unaffected by light
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg Weight/m ² Thickness: 6mm Thickness: 7.8mm Thickness: 8.5mm		11.9kg 16.28kg 17.91kg

Samples Service

Technical Helpline

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction is the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potentia and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (28/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Engl. No. 15600432. © 2025 Johnson Tiles. All rights reserved.

