# **COUNTRY RUSTIC** PRODUCT DATA SHEET



 $\mathcal{O}$  Recycled Content Up to 20% **Country Rustic** Range Category Collection Short Code CRFA Colour Apple Green **Gloss - Rustic Structure** Finish Wall Suitability Internal Only Floor Suitability -Wet Barefoot -Material Glazed Ceramic Classificiation BIII CSV

### **Physical Properties** Test / Standard Requirement Length/Width ±0.5%≤ ± 2mm EN ISO 10545-4 Straightness of Sides ±0.3% ≤ ± 1.5mm Minton Hollins Collection EN ISO 10545-2 Rectangularity $\pm 0.5\% \leq \pm 2mm$ EN ISO 10545-2 Surface Flatness $\pm 0.5\% \leq \pm 2mm$ EN ISO 10545-2 Warpage ±0.5%≤ ± 2mm EN ISO 10545-2 $\bigcirc$ Water Absorption 10% to 20% EN ISO 10545-3 Modulus of Rupture Ave 15N/mm<sup>2</sup> EN ISO 10545-4 潫 Frost Resistance N/A Not Applicable ٧I **Chemical Resistance**

Æ

100x100x9.5mm

## Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

**Technical Helpline** 

Tel: +44 (0)1782 524 111 Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com

±0.25% ±0.15% ± 0.4% ±0.2% 0.30% 15% to 17% 25N/mm<sup>2</sup> Not suitable Æ Min Class B Class A-B (better) EN ISO 10545-13 Stain Resistance Min Class 3 Class 3 (better) EN ISO 10545-14 **Crazing Resistance** Pass Pass EN ISO 10545-11 UV Colour Resistance Unaffected by light

Scratch Hardness ≥3 4 BS6431:Part13/EN101 Class A1 Non Fire Rating Combustible

### www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 significant reduction and 36+ represents a low slip potential. All rights reserved. No. 15600452.0 2025 Johnson Tiles. All rights reserved.





Test Result