


# COUNTRY RUSTIC PRODUCT DATA SHEET



## Available Sizes

100x100x9.5mm  
150x150x9.5mm

## Samples Service

Tel: +44 (0)1782 524 043  
Fax: +44 (0)1782 577 379  
Email: [samples@johnson-tiles.com](mailto:samples@johnson-tiles.com)

## Technical Helpline

Tel: +44 (0)1782 524 111  
Fax: +44 (0)1782 577 379  
Email: [techadvice@johnson-tiles.com](mailto:techadvice@johnson-tiles.com)

[www.johnson-tiles.com](http://www.johnson-tiles.com)

Recycled Content	Up to 20%
Range	Country Rustic
Category	
Collection	Minton Hollins Collection
Short Code	CRF2A
Colour	Cream
Finish	Gloss - Rustic Structure
Wall Suitability	Internal Only
Floor Suitability	-
Wet Barefoot	-
Material	Glazed Ceramic
Classification	BIII
CSV	VI

Physical Properties		
Test / Standard	Requirement	Test Result
<b>Length/Width</b> EN ISO 10545-4	$\pm 0.5\% \leq \pm 2\text{mm}$	$\pm 0.25\%$
<b>Straightness of Sides</b> EN ISO 10545-2	$\pm 0.3\% \leq \pm 1.5\text{mm}$	$\pm 0.15\%$
<b>Rectangularity</b> EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	$\pm 0.4\%$
<b>Surface Flatness</b> EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	$\pm 0.2\%$
<b>Warpage</b> EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	0.30%
<b>Water Absorption</b> EN ISO 10545-3	10% to 20%	15% to 17%
<b>Modulus of Rupture</b> EN ISO 10545-4	Ave 15N/mm <sup>2</sup>	25N/mm <sup>2</sup>
<b>Frost Resistance</b> Not Applicable	N/A	Not suitable
<b>Chemical Resistance</b> EN ISO 10545-13	Min Class B	Class A-B (better)
<b>Stain Resistance</b> EN ISO 10545-14	Min Class 3	Class 3 (better)
<b>Crazing Resistance</b> EN ISO 10545-11	Pass	Pass
<b>UV Colour Resistance</b>		Unaffected by light
<b>Scratch Hardness</b> BS6431:Part 13/EN101	$\geq 3$	4
<b>Fire Rating</b>		Class A1 Non Combustible

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (30/04/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.