COUNTY PRODUCT DATA SHEET



Test Result

±0.25%

±2.5%

± 0.15%

16kg



Available Sizes 300x200x8mm

arrho Recycled Content	Up to 20%
	Country
Range	County
Category	Stone
Collection	Intro Collection
Short Code	CNY03A
Colour	Natural Grey
Finish	Matt
Wall Suitability	Internal Only
Floor Suitability	-
Wet Barefoot	-
Material	Glazed Ceramic
Classificiation	BIII
Light Reflectance Value	53.00
CSV	V2

h	Natural Grey Matt	-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	± 0.4%
. Suitability	Internal Only	$\begin{array}{ c c }\hline \downarrow \\ \hline \uparrow \uparrow \\ \end{array}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.2%
r Suitability	-		Water Absorption EN ISO 10545-3	10% to 20%	15% to 17%
Barefoot	-		Modulus of Rupture	Ave I5N/mm²	25N/mm²
erial	Glazed Ceramic		EN ISO 10545-4	<i>.</i>	
sificiation	BIII	 	Frost Resistance Not Applicable	N/A	Not suitable
t Reflectance Value	53.00		Chemical Resistance EN ISO 10545-13	Min Class B	Class A-B (better)
	V2				
			Stain Resistance EN ISO 10545-14	Min Class 3	Class 3 (better)
			Fire Rating		Class A1 Non Combustible
		kg	Weight/m ²		

Thickness 8mm

Physical Properties Test / Standard

Length/Width

EN ISO 10545-2 Thickness

EN ISO 10545-2 Straightness of Sides

EN ISO 10545-2

Requirement

±0.5%≤ ± 2mm

±10%≤ ± 0.5mm

 $\pm 0.3\% \le \pm 1.5$ mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com



