
ECHO PRODUCT DATA SHEET





Available Sizes 300x200x8mm

$oldsymbol{arrho}$ Recycled Content	Up to 20%
Range	Echo
Category	Stone
Collection	Intro Collection
Short Code	ECHO2A
Colour	Shadow
Finish	Gloss
Wall Suitability	Internal Only
Floor Suitability	-
Wet Barefoot	-
Material	Glazed Ceramic
Classificiation	BIII
Light Reflectance Value	64.00
CSV	V2

inish	Gloss			EN ISO 10545-2	
Vall Suitability	Internal Only	-		Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2
loor Suitability	-	_		Water Absorption EN ISO 10545-3	10% to 20%
Vet Barefoot	-		, °	Modulus of Rupture	
1aterial	Glazed Ceramic		EN ISO 10545-4	Ave I5N/m	
Classificiation	BIII	-	<u>*</u>	Frost Resistance Not Applicable	N/A
ight Reflectance Value	64.00	_		Chemical Resistance	Min Class B
CSV	V2	-		EN ISO 10545-13	
		-		Stain Resistance EN ISO 10545-14	Min Class 3

Samp	les	Ser	vice
------	-----	-----	------

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Physical Properties				
Test / Standard Requirement		Test Result		
Length/Width EN ISO 10545-2	±0.5%≤ ± 2mm	±0.25%		
Thickness EN ISO 10545-2	±10%≤±0.5mm	±2.5%		
Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	± 0.15%		
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	± 0.4%		
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.2%		
Water Absorption EN ISO 10545-3	10% to 20%	15% to 17%		
Modulus of Rupture EN ISO 10545-4	Ave I5N/mm²	25N/mm²		
Frost Resistance Not Applicable	N/A	Not suitable		
Chemical Resistance EN ISO 10545-13	Min Class B	Class A-B (better)		
Stain Resistance EN ISO 10545-14	Min Class 3	Class 3 (better)		
Fire Rating		Class A1 Non Combustible		
kg Weight/m² Thickness 8mm		16kg		



