
ECOSTONE PRODUCT DATA SHEET





Available Sizes 300x300x10mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

	Up to 90%	
Range	Ecostone	
Category	Stone, Mosaic, Floor Tiles,	
	PTV 36+ Tiles	
Collection	Absolute Collection	
Short Code	ECO2MB	
Colour	Bronze	
Finish	Natural - Strip Mosaic	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	10.00	
CSV	V4	
PTV (96)	Wet 36+ Dry 36+	
PTV (55)	-	
R Value	10	
Wet Ramp	-	
PEI	II	
Traffic	Domestic	

Physi	Physical Properties				
Test / Standard		Requirement	Test Result		
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass		
$\begin{array}{ c c }\hline \downarrow \\ \hline \uparrow \\ \hline \end{array}$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass		
-]+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass		
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass		
	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass		
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%		
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass		
	Thermal Shock EN ISO 10545-9	Pass	Pass		
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant		
	Chemical Resistance EN ISO 10545-13	Min Class B	Pass		
	Stain Resistance EN ISO 10545-14	Min Class 3	Pass		
~~~~ ~~~~~	UV Colour Resistance		Unaffected by light		
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible		
kg	Weight/m² Thickness: I 0mm Thickness: I 1mm		18.16kg 25.1kg		

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance avalues provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance of slip liked to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a line of slip slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (22/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 1.560/437 @ 2025 in Johnson Tiles All rights reserved.

