EDEN PRODUCT DATA SHEET





Available Sizes

2600x1200x6mm 1200x600x9.3mm 1200x1200x9.3mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Recycled Content	Up to 40%	
lange	Eden	
Category	Marble, Floor Tiles	
Collection	Select Collection	
Short Code	EDN02P	
Colour	Silver	
Finish	Polished	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
ight Reflectance Value	70.00	
CSV	V2	
PTV (96)	Wet 0-24 Dry 36+	
PTV (55)	-	
R Value	-	
Wet Ramp	-	
PEI	IV	
raffic	Commercial	

Physical Properties				
Test / Standard		Requirement	Test Result	
Length/Widtl EN ISO 10545		±0.6%≤ ± 2mm	Pass	
Thickness EN ISO 10545	-2	±5%≤ ± 0.5mm	Pass	
Straightness EN ISO 10545		±0.5% ≤ ± 1.5mm	Pass	
Rectangularit EN ISO 10545	•	±0.5% ≤ ± 2mm	Pass	
Surface Flatn ↑↑ EN ISO 10545		±0.5% ≤ ± 2mm	Pass	
Water Absorp		≤0.5%	Pass	
Modulus of R EN ISO 10545	-	≥35N/mm²	Pass	
Thermal Shoo EN ISO 10545		Pass	Pass	
Frost Resista EN ISO 10545		Resistant	Resistant	
Chemical Res EN ISO 10545		Min Class B	Pass	
Stain Resistar EN ISO 10545		Min Class 3	Pass	
UV Colour Re	sistance		Unaffected by light	
Fire Rating Not Applicabl	e	N/A	Class A I FL Non Combustible	
Weight/m² Thickness:6m Thickness:9.3			16.67kg 21.53kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential.

