


# ESSENTIAL PRODUCT DATA SHEET



## Available Sizes

1200x590x10mm  
990x990x10mm  
590x590x9.5mm  
600x300x8.7mm  
450x450x8.5mm

## Samples Service

Tel: +44 (0)1782 524 043  
Fax: +44 (0)1782 577 379  
Email: [samples@johnson-tiles.com](mailto:samples@johnson-tiles.com)

## Technical Helpline

Tel: +44 (0)1782 524 111  
Fax: +44 (0)1782 577 379  
Email: [techadvice@johnson-tiles.com](mailto:techadvice@johnson-tiles.com)

[www.johnson-tiles.com](http://www.johnson-tiles.com)

Range	Essential
Category	Concrete, Floor Tiles, PTV 36+ Tiles
Collection	Select Collection
Short Code	ESS01N
Colour	Ivory
Finish	Natural
Wall Suitability	Internal & External
Floor Suitability	Internal Only
Wet Barefoot	-
Material	Glazed Porcelain
Classification	Bla
Light Reflectance Value	64.00
CSV	V3
PTV (96)	Wet 36+ Dry 36+
PTV (55)	-
R Value	10
Wet Ramp	C
PEI	IV
Traffic	Commercial

Physical Properties		
Test / Standard	Requirement	Test Result
 <b>Length/Width</b> EN ISO 10545-2	$\pm 0.6\% \leq \pm 2\text{mm}$	Pass
 <b>Thickness</b> EN ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	Pass
 <b>Straightness of Sides</b> EN ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	Pass
 <b>Rectangularity</b> EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass
 <b>Surface Flatness</b> EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass
 <b>Water Absorption</b> EN ISO 10545-3	$\leq 0.5\%$	Pass
 <b>Modulus of Rupture</b> EN ISO 10545-4	$\geq 35\text{N/mm}^2$	Pass
 <b>Frost Resistance</b> EN ISO 10545-12	Resistant	Resistant
 <b>Chemical Resistance</b> EN ISO 10545-13	Min Class B	Min Class B
 <b>Stain Resistance</b> EN ISO 10545-14	Min Class 3	Min Class 3
 <b>Fire Rating</b> Not Applicable	N/A	Class A1 FL Non Combustible
 <b>Weight/m<sup>2</sup></b> Thickness: 8.5mm Thickness: 8.7mm Thickness: 9.5mm Thickness: 10mm		17.68kg 18.19kg 19.77kg 22.1kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (11/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.