FUJI PRODUCT DATA SHEET





Available Sizes 1200x600x10.7mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Recycled Content	Up to 60%	
Range	Fuji	
Category	Marble, Floor Tiles	
Collection	Absolute Collection	
Short Code	FUJ02M	
Colour	Calacatta	
Finish	Matt	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	62.00	
CSV	V2	
PTV (96)	Wet 25-35 Dry 36+	
PTV (55)	-	
R Value	-	
Wet Ramp	-	
PEI	IV	
Traffic	Commercial	

Physi	cal Properties		
Test /	Standard	Requirement	Test Result
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
$\begin{array}{ c c } \hline \downarrow \\ \hline \uparrow \\ \hline \end{array}$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
-]+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
<u>↓</u>	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²
	Thermal Shock EN ISO 10545-9	Pass	Pass
<u>*</u>	Frost Resistance EN ISO 10545-12	Resistant	Resistant
	Chemical Resistance EN ISO 10545-13	Min Class B	Min Class B
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~	UV Colour Resistance		Unaffected by light
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg	Weight/m ² Thickness:9.9mm Thickness:10.7mm Thickness:11.5mm		21.9kg 24kg 25.95kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. All figures are accurate at the time of this data sheets creation (30/04/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Englan No. 15600432. © 2025 Johnson Tiles. All rights reserved.

