FUJI PRODUCT DATA SHEET



		36+ Tiles
	Collection	Absolute Collection
	Short Code	FUJ02N
	Colour	Calacatta
	Finish	Natural
	Wall Suitability	Internal & External
1	Floor Suitability	Internal Only
Available Sizes	Wet Barefoot	-
1200x600x10.7mm	Material	Glazed Porcelain
	Classificiation	Bla
	Light Reflectance Value	62.00
	CSV	V2
	PTV (96)	Wet 36+ Dry 36+
Samples Service	PTV (55)	-
Tel: +44 (0) 782 524 043 Fax: +44 (0) 782 577 379	R Value	-
Email: samples@johnson-tiles.com	Wet Ramp	-
Technical Helpline Tel: +44 (0)1782 524 111	PEI	IV
Fax: +44 (0) 782 577 379 Email: techadvice@johnson-tiles.com	Traffic	Commercial

Range Category Up to 60%

Marble, Floor Tiles, PTV

Fuji

Physical Properties		
Fest / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
→ Thickness ← EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
→ Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Min Class B
Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
UV Colour Resistance		Unaffected by light
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg Weight/m ² Thickness:9.9mm Thickness:10.7mm Thickness:11.5mm		21.9kg 24kg 25.95kg

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (30/04/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.



