GALLOWAY PRODUCT DATA SHEET



Floor Suitability Internal Only Wet Barefoot -Material Glazed Porcelain Classificiation Bla Light Reflectance Value 42.00 CSV ٧3 PTV (96) Wet 25-35 Dry 36+ PTV (55) -R Value _ Wet Ramp -PEI IV Traffic Commercial

 \varnothing Recycled Content

Range

Category Collection

Short Code

Wall Suitability

Colour

Finish

Up to 10%

Galloway

GLW01M

Birch

Wood, Floor Tiles

Absolute Collection

Natural - Maise Décor

Internal & External

| Physical Properties | | |
|---|-----------------|---------------------------------|
| Test / Standard | Requirement | Test Result |
| Length/Width EN ISO 10545-2 | ±0.6%≤ ± 2mm | ±0.3% |
| Thickness EN ISO 10545-2 | ±5%≤ ± 0.5mm | ±3% |
| Straightness of Sides EN ISO 10545-2 | ±0.5% ≤ ± 1.5mm | ±0.3% |
| Rectangularity EN ISO 10545-2 | ±0.5% ≤ ± 2mm | ±0.3% |
| ↓ Surface Flatness ↑ ↑ EN ISO 10545-2 | ±0.5% ≤ ± 2mm | ±0.3% |
| Water Absorption EN ISO 10545-3 | ≤0.5% | ≤0.1% |
| Modulus of Rupture EN ISO 10545-4 | ≥35N/mm² | ≥45N/mm² |
| Thermal Shock EN ISO 10545-9 | Pass | Pass |
| Frost Resistance EN ISO 10545-12 | Resistant | Resistant |
| Chemical Resistance EN ISO 10545-13 | Min Class B | Min Class B |
| Stain Resistance EN ISO 10545-14 | Min Class 3 | Min Class 3 |
| Fire Rating Not Applicable | N/A | Class A FL Non Combustible |
| kg Weight/m ² Thickness: 10.5mm | | 22.6kg |

Samples Service

Available Sizes

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in stip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies at moderate slip potential and 36r represents a low slip potential. All rightres are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. 6 2023 Johnson Tiles. All rights reserved.



