GALLOWAY PRODUCT DATA SHEET





Available Sizes

1190x200x10.5mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Recycled Content	Up to 10%	
Range	Galloway	
Category	Wood, Floor Tiles	
Collection	Absolute Collection	
Short Code	GLW02N	
Colour	Oak	
Finish	Natural	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	40.00	
CSV	V3	
PTV (96)	Wet 25-35 Dry 36+	
PTV (55)	-	
R Value	-	
Wet Ramp	-	
PEI	IV	
Traffic	Commercial	

Physical Properties				
Test /	Standard	Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.3%	
<u></u>	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	±3%	
- +	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.3%	
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
\downarrow	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%	
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥45N/mm²	
	Thermal Shock EN ISO 10545-9	Pass	Pass	
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant	
	Chemical Resistance EN ISO 10545-13	Min Class B	Min Class B	
	Stain Resistance EN ISO 10545-14	Min Class 3	Min Class 3	
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg =	Weight/m² Thickness: 10.5mm		22.6kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a lips slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (30/04/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Englance. No 1560/04/2025 and 1560/04/2025 are considered in Englance.

