GALLOWAY PRODUCT DATA SHEET





Available Sizes 600x600x9.2mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

| arrho Recycled Content | Up to 10% | |
|-------------------------|-------------------------|--|
| Range | Galloway | |
| Category | Wood, Floor Tiles | |
| Collection | Absolute Collection | |
| Short Code | GLW03V | |
| Colour | Walnut | |
| Finish | Natural - Chevron Décor | |
| Wall Suitability | Internal & External | |
| Floor Suitability | Internal Only | |
| Wet Barefoot | - | |
| Material | Glazed Porcelain | |
| Classificiation | Bla | |
| Light Reflectance Value | 15.00 | |
| CSV | V3 | |
| PTV (96) | Wet 25-35 Dry 36+ | |
| PTV (55) | - | |
| R Value | - | |
| Wet Ramp | - | |
| PEI | III | |
| Traffic | Light Commercial | |

| Physical Properties | | |
|---|-----------------|---------------------------------|
| Test / Standard | Requirement | Test Result |
| Length/Width EN ISO 10545-2 | ±0.6%≤ ± 2mm | ±0.3% |
| Thickness EN ISO 10545-2 | ±5%≤ ± 0.5mm | ±3% |
| Straightness of Sides EN ISO 10545-2 | ±0.5% ≤ ± 1.5mm | ±0.3% |
| Rectangularity EN ISO 10545-2 | ±0.5% ≤ ± 2mm | ±0.3% |
| Surface Flatness EN ISO 10545-2 | ±0.5% ≤ ± 2mm | ±0.3% |
| Water Absorption EN ISO 10545-3 | ≤0.5% | ≤0.1% |
| Modulus of Rupture EN ISO 10545-4 | ≥35N/mm² | ≥45N/mm² |
| Thermal Shock EN ISO 10545-9 | Pass | Pass |
| Frost Resistance EN ISO 10545-12 | Resistant | Resistant |
| Chemical Resistance EN ISO 10545-13 | Min Class B | Min Class B |
| Stain Resistance EN ISO 10545-14 | Min Class 3 | Min Class 3 |
| Fire Rating Not Applicable | N/A | Class A I FL Non Combustible |
| Weight/m² Thickness: 10.5mm | | 22.6kg |

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 156004372. © 2025 Johnson Tiles. All rights reserved.

