
GLADEMOOR PRODUCT DATA SHEET





Available Sizes

600x600x9.2mm 600x300x9.2mm 450x450x9.2mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

 ${\bf Email: samples@johnson-tiles.com}$

Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Ø Recycled Content	Up to 10%	
Range	Glademoor	
Category	Stone, Floor Tiles, PTV 36+	
	Tiles	
Collection	Select Collection	
Short Code	GLA01G	
Colour	Bone	
Finish	Grip	
Wall Suitability	Internal & External	
Floor Suitability	Internal & External	
Wet Barefoot	Yes	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	86.00	
CSV	V3	
PTV (96)	Wet 36+ Dry 36+	
PTV (55)	Wet 36+	
R Value	11	
Wet Ramp	С	
PEI	v	
Traffic	Heavy Commercial	

Physical Properties			
Test / Standard		Requirement	Test Result
Length/Widt EN ISO 10545		±0.6%≤ ± 2mm	±0.3%
Thickness EN ISO 10545	i-2	±5%≤ ± 0.5mm	±3%
Straightness EN ISO 10545		±0.5% ≤ ± 1.5mm	±0.3%
Rectangulari EN ISO 10545	•	±0.5% ≤ ± 2mm	±0.3%
♦ Surface Flatment FN ISO 10545		±0.5% ≤ ± 2mm	±0.3%
Water Absorption EN ISO 10545		≤0.5%	≤0.1%
Modulus of R EN ISO 10545	-	≥35N/mm²	≥45N/mm²
Thermal Shoo EN ISO 10545		Pass	Pass
Frost Resista EN ISO 10545		Resistant	Resistant
Chemical Res EN ISO 10545		Min Class B	Min Class B
Stain Resista EN ISO 10545		Min Class 3	Min Class 3
UV Colour Re	esistance		Unaffected by light
Fire Rating Not Applicable	Le	N/A	Class A I FL Non Combustible
Weight/m² Thickness: 9.2 Thickness: 10			21.4kg 23.09kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a light slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (17/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Englan No. 1560/0437, © 2025 Inbnson Tiles All rights reserved.

