GLADEMOOR PRODUCT DATA SHEET



${\cal O}$ Recycled Content	Up to 10%
Range	Glademoor
Category	Stone, Mosaic, Floor Tile
Collection	Select Collection
Short Code	GLA3NM
Colour	Sand
Finish	Natural - Square Mosaic
Wall Suitability	Internal & External
Floor Suitability	Internal Only
Wet Barefoot	-
Material	Glazed Porcelain
Classificiation	Bla
Light Reflectance Value	66.00
CSV	٧3
PTV (96)	Wet 0-24 Dry 36+
PTV (55)	-
R Value	-
Wet Ramp	-
PEI	ν
Traffic	Heavy Commercial

est / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.3%
↓ Thickness ↑ EN ISO 10545-2	±5%≤ ± 0.5mm	±3%
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.3%
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%
Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥45N/mm²
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Min Class B
Stain Resistance EN ISO 10545-14	Min Class 3	Min Class 3
UV Colour Resistance		Unaffected by light
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
Weight/m ² Thickness: 9.2mm Thickness: 10.5mm		21.4kg 23.09kg

Samples Service

Available Sizes

300x300x9.2mm (50x50mm)

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.



epd