HEX25 PRODUCT DATA SHEET



Available Sizes

250x220x10mm (Hexagon)

Samples Service

Tel: +44 (0) | 782 524 043 Fax: +44 (0) | 782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Ø Recycled Content	Up to 10%	
Range	Hex25	
Category	Colour, Pattern, Shape,	
	Floor Tiles	
Collection	Absolute Collection	
Short Code	HEX19F	
Colour	Fantasy Mix	
Finish	Natural	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
CSV	V2	
PTV (96)	Wet 0-24 Dry 36+	
PTV (55)	-	
R Value	9	
Wet Ramp	-	
PEI	IV	
Traffic	Commercial	

Physical Properties			
Test / Standard		Requirement	Test Result
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
↓	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
- +	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
$\boxed{ \begin{array}{c} \downarrow \\ \hline \uparrow \uparrow \end{array} }$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²
	Thermal Shock EN ISO 10545-9	Pass	Pass
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant
	Chemical Resistance EN ISO 10545-13	Min Class B	Pass
	Stain Resistance EN ISO 10545-14	Min Class 3	Pass
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg	Weight/m² Thickness: 9mm		21kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and four represents a low, with productional All figures are accurate at the time of this data start creation (19/05/1073). Debogan Tiles Limited Heavy of Streat Tunstall All figures are accurate at the time of the idata starting and maintenance will lead to a significant reduction in the slip resistance of any tiles.

