KERASTAR PRODUCT DATA SHEET

\mathscr{O} Recycled Content	Up to 6%
Range	Kerastar
Category	Colour, Floor Tiles
Collection	Intro Collection
Short Code	KEM554
Colour	Mint
Finish	Matt
Wall Suitability	Internal & External
Floor Suitability	Internal Only
Wet Barefoot	-
Material	Un-glazed Porcelain
Classificiation	Bla
Light Reflectance Value	41.00
CSV	VI
PTV (96)	Wet 25-35 Dry 36+
PTV (55)	-
R Value	9
Wet Ramp	-
PEI	-
Traffic	Commercial

-	Physical Properties				
Test / Standard		Requirement	Test Result		
${\longleftrightarrow}$	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.3%		
$\stackrel{\rightarrow}{[]}$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	±3%		
+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.3%		
<u> </u>	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%		
$\stackrel{\mathbf{h}}{\underset{\mathbf{h}}{\overset{\mathbf{h}}}}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	± 0.3%		
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%		
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥45N/mm²		
<u>**</u>	Thermal Shock EN ISO 10545-9	Pass	Pass		
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant		
B	Chemical Resistance EN ISO 10545-13	No Visible Effect	Pass		
	Stain Resistance EN ISO 10545-14		≥Class 2		
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible		
kg	Weight/m ²				
	Thickness: 7.6mm		16.78kg		
	Thickness: 8.3mm		18.56kg		
	Thickness: 8.5mm		19.12kg		
	Thickness: 9.2mm		21.67kg		
	Thickness: 9.8mm		21.12kg		
	Thickness: 10.5mm Thickness: 14mm		24.37kg		
	mickness: 14mm		31.39kg		

Available Sizes

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (30/04/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

JOHNSON TILES

epd