KOTTO PRODUCT DATA SHEET



Available Sizes

300x150x6mm 330x330x7.2mm 605x305x7.8mm 455x455x8mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Recycled Content	Up to 10%	
lange	Kotto	
Category	Stone, Floor Tiles	
Collection	Absolute Collection	
Short Code	KOT02N	
Colour	Beige	
Finish	Natural	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla & Blb	
Light Reflectance Value	31.00	
CSV	V4	
PTV (4S)	Wet 25-35 Dry 36+	
PTV (TRL)	-	
R Value	-	
Wet Ramp	-	
PEI	III	
Traffic	Light Commercial	

Physical Properties		
Test / Standard	Requirement	Test Result
Length/Width EN ISO I 0545-2	±0.6%≤ ± 2mm	Pass
Thickness EN ISO I 0545-2	±5%≤ ± 0.5mm	Pass
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
Water Absorption EN ISO 10545-3	0.5% to 3%	Pass
Modulus of Rupture EN ISO 10545-4	≥30N/mm²	Pass
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Class A
Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
UV Colour Resistance		Unaffected by light
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg Weight/m² Thickness: 6mm		12.61kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be sm resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a m

