KOTTO PRODUCT DATA SHEET



Available Sizes 330x330x7.2mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Recycled Content	Up to 10%	
Range	Kotto	
Category	Stone, Floor Tiles, PTV 36+	
	Tiles	
Collection	Absolute Collection	
Short Code	КОТ03G	
Colour	Grey	
Finish	Grip	
Wall Suitability	Internal & External	
Floor Suitability	Internal & External	
Wet Barefoot	Yes	
Material	Glazed Porcelain	
Classificiation	Bla & Blb	
Light Reflectance Value	38.00	
CSV	V4	
PTV (96)	Wet 36+ Dry 36+	
PTV (55)	Wet 36+	
R Value	12	
Wet Ramp	С	
PEI	III	
Traffic	Light Commercial	

Physical Properties			
Test /	Standard	Requirement	Test Result
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
<u></u>	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
-]+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
$ \\ \boxed{ \\ \uparrow \uparrow } \\ $	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	≤0.5%	Pass
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass
	Thermal Shock EN ISO 10545-9	Pass	Pass
<u>*</u>	Frost Resistance EN ISO 10545-12	Resistant	Resistant
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
	UV Colour Resistance		Unaffected by light
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg	Weight/m² Thickness: 7.2mm Thickness: 7.8mm Thickness: 8mm		15.78kg 16.9kg 18.39kg

www.joimson-tites.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in Englar No. 15600432. © 2025 Johnson Tiles. All rights reserved.

