LAGOS PRODUCT DATA SHEET



Available Sizes 330x330x7.2mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Ø Recycled Content	Up to 10%	
Range	Lagos	
Category	Stone, Structure, Floor	
	Tiles	
Collection	Intro Collection	
Short Code	LAGOIF	
Colour	Dark Grey	
Finish	Matt - Rock Structure	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	13.00	
CSV	VI	
PTV (96)	Wet 0-24 Dry 36+	
PTV (55)	-	
R Value	-	
Wet Ramp	-	
PEI	I	
Traffic	Commercial	

Physical Properties			
Test / Standard	Requirement	Test Result	
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%	
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²	
Abrasion Resistance EN ISO 10545-6	≤175mm³	≤175mm³	
Frost Resistance EN ISO 10545-12	Resistant	Resistant	
Chemical Resistance EN ISO 10545-13	Min Class B	Pass	
Stain Resistance EN ISO 10545-14	Min Class 3	Pass	
Fire Rating		Class A I FL Non Combustible	
kg Weight/m² Thickness: 8.5mm		18.1kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential

