LUXX PRODUCT DATA SHEET



Range	Luxx
Category	Marble, Floor Tiles
Collection	Absolute Collection
Short Code	LUX04N
Colour	Crema Marble
Finish	Natural
Wall Suitability	Internal & External
Floor Suitability	Internal Only
Wet Barefoot	-
Material	Glazed Porcelain
Classificiation	Bla
CSV	V2
PTV (96)	Wet 25-35 Dry 36+
PTV (55)	-
R Value	9
Wet Ramp	Α
PEI	-
Traffic	Commercial

Physical Properties				
Test /	Standard	Requirement	Test Result	
${\longleftrightarrow}$	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
$\rightarrow \square \diamond$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass	
+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
${\underset{ \ \ }{ }}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%	
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥45N/mm²	
- Mark	Thermal Shock EN ISO 10545-9	Pass	Pass	
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant	
B	Chemical Resistance EN ISO 10545-13	Min Class B	Min Class B	
	Stain Resistance EN ISO 10545-14	Min Class 3	Min Class 3	
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg	Weight/m ² Thickness: 6.5mm		15.8kg	

Samples Service

Available Sizes 1200x1200x6.5mm 600x600x6.5mm 1200x600x6.5mm

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

