MINERALS PRODUCT DATA SHEET



and the second	the second second second second		The VERSION STREET, ST	and the second second	and a second and the second and the		
			A			Range	Minerals
		2		8		Category	Stone, Mosaic, Floor Tiles
			1.	-		Collection	Absolute Collection
						Short Code	MIN4NM
						Colour	Flint
						Finish	Natural - 50mm Square
14							Mosaic
					8	Wall Suitability	Internal & External
			A			Floor Suitability	Internal Only
Availabl	e Sizes					Wet Barefoot	-
)x9mm (50x	50mm)				Material	Porcelain
						Classificiation	Bla
						Light Reflectance Value	32.00
						CSV	V2
						PTV (96)	Wet 25-35 Dry 36+
Samples	s Service					PTV (55)	-
Tel: +44 (0)1782 524 043 Fax: +44 (0)1782 577 379						R Value	9
Email: samples@johnson-tiles.com						Wet Ramp	Α
Technical Helpline						PEI	-
Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com						Traffic	Commercial
Lmait: te	cinacivice@j	unnson-t	.ites.com				

Up to 30%

Physical Properties		
Test / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
	±5%≤ ± 0.5mm	Pass
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
→ Surface Flatness ► N ISO 10545-2	±0.5% ≤ ± 2mm	Pass
Water Absorption EN ISO 10545-3	≤0.5%	≤0.5%
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Pass
Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg Weight/m ² Thickness: 6mm Thickness: 9mm Thickness: 20mm		14.09kg 21.19kg 45.85kg

Technical Helpline

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

