MINERALS PRODUCT DATA SHEET

Available Sizes

300x300x9mm

Samples Service

Tel: +44 (0)1782 524 043
Fax: +44 (0)1782 577 379
Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0)1782 524 111
Fax: +44 (0)1782 577 379
Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Recycled Content	**Up to 30%**
Range	**Minerals**
Category	**Stone, Mosaic, Floor Tiles, PTV 36+ Tiles**
Collection	**Absolute Collection**
Short Code	**MIN6BM**
Colour	**Pebble**
Finish	**Bush Hammered - Mixed Strip Mosaic**
Wall Suitability	**Internal & External**
Floor Suitability	**Internal & External**
Wet Barefoot	**Yes**
Material	**Porcelain**
Classificiation	**Bla**
Light Reflectance Value	**42.00**
CSV	**V2**
PTV (96)	**Wet 36+ Dry 36+**
PTV (55)	**Wet 36+**
R Value	**10**
Wet Ramp	**B**
PEI	**-**
Traffic	**Commercial**

Physical Properties

Test / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	**Pass**
Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	**Pass**
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	**Pass**
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	**Pass**
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	**Pass**
Water Absorption EN ISO 10545-3	≤0.5%	**≤0.5%**
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	**≥35N/mm²**
Thermal Shock EN ISO 10545-9	Pass	**Pass**
Frost Resistance EN ISO 10545-12	Resistant	**Resistant**
Chemical Resistance EN ISO 10545-13	Min Class B	**Pass**
Stain Resistance EN ISO 10545-14	Min Class 3	**Class 5**
Fire Rating Not Applicable	N/A	**Class A1FL Non Combustible**
Weight/m²		
Thickness: 6mm		**14.09kg**
Thickness: 9mm		**21.19kg**
Thickness: 20mm		**45.85kg**

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (12/10/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registed in England No. 15600432. © 2024 Johnson Tiles. All rights reserved.

Est. 1901 JOHNSON TILES