## MINERALS PRODUCT DATA SHEET

A start of the start of the
and the second
and the second

	Category	Stone, Mosaic, Floor Tiles,
		PTV 36+ Tiles
	Collection	Absolute Collection
	Short Code	MIN6BM
	Colour	Pebble
	Finish	Bush Hammered - Mixed
the second s		Strip Mosaic
	Wall Suitability	Internal & External
Available Sizes	Floor Suitability	Internal & External
300x300x9mm	Wet Barefoot	Yes
	Material	Porcelain
	Classificiation	Bla
	Light Reflectance Value	42.00
	CSV	V2
Samples Service	PTV (96)	Wet 36+ Dry 36+
Tel: +44 (0)   782 524 043	PTV (55)	Wet 36+
Fax: +44 (0)1782 577 379 Email: samples@johnson-tiles.com	R Value	10
Technical Helpline	Wet Ramp	В
Tel: +44 (0)   782 524       Fax: +44 (0)   782 577 379	PEI	-
Email: techadvice@johnson-tiles.com	Traffic	Commercial
www.johnson-tiles.com		

 $\varnothing$  Recycled Content

Range

Up to 30%

Minerals

sical Properties			
t / Standard	Requirement	Test Result	
Length/Width	±0.6%≤ ± 2mm	Pass	
EN ISO 10545-2			
Thickness	±5%≤ ± 0.5mm	Pass	
EN ISO 10545-2			
Straightness of Sides	±0.5% ≤ ± 1.5mm	Pass	
EN ISO 10545-2	10.0% 2 1 1.01111	1 455	
Rectangularity	±0.5% ≤ ± 2mm	Pass	
EN ISO 10545-2	10.5% 2 1 21111	1 435	
Surface Flatness	±0.5% ≤ ± 2mm	Pass	
EN ISO 10545-2	10.5% 2 1 21111	1 435	
Water Absorption	≤0.5%	≤0.5%	
EN ISO 10545-3	20.3 %	20.3 %	
Modulus of Rupture	≥35N/mm²	≥35N/mm²	
EN ISO 10545-4	23310/11111	23314/11111	
Thermal Shock	Pass	Pass	
EN ISO 10545-9	1 835	1 455	
Frost Resistance	Resistant	Resistant	
EN ISO 10545-12	Resistant	Resistant	
Chemical Resistance	Min Class B	Pass	
EN ISO 10545-13		Fass	
Stain Resistance	Min Class 3	Class 5	
EN ISO 10545-14	Thin Class 5	Class 5	
Fire Rating	N/A	Class A I FL Nor	
Not Applicable	IN/A	Combustible	
Weight/m <sup>2</sup>			
Thickness: 6mm Thickness: 9mm		14.09kg	
		21.19kg	

## www.johnson-ti

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.



