
MONOCHROME PRODUCT DATA SHEET



| ${\cal O}$ Recycled Content | Up to 20% |
|-----------------------------|-------------------|
| Range | Monochrome |
| Category | Colour |
| Collection | Select Collection |
| Short Code | PRG6 |
| Colour | Black |
| Finish | Gloss |
| Wall Suitability | Internal Only |
| Floor Suitability | - |
| Wet Barefoot | - |
| Material | Glazed Ceramic |
| Classificiation | BIII |
| Light Reflectance Value | 4.00 |
| CSV | VI |

| Physical Properties | | | | |
|------------------------------------------|-----|-------------------------|------------------------------|--|
| Test / Standard | | Requirement | Test Result | |
| Length/Wid EN ISO 1054 | | ±0.5%≤ ± 2mm | ±0.25% | |
| Thickness Thickness EN ISO 1054 | 5-2 | ±10%≤±0.5mm | ±2.5% | |
| Straightnes EN ISO 1054 | | ±0.3% ≤ ± 1.5mm | ± 0.15% | |
| Rectangular EN ISO 1054 | | ±0.5% ≤ ± 2mm | ± 0.4% | |
| J Surface Flat ↑ ↑ EN ISO 1054 | | ±0.5% ≤ ± 2mm | ±0.2% | |
| Water Abso EN ISO 1054 | - | 10% to 20% | 15% to 17% | |
| Modulus of EN ISO 1054 | • | Ave I5N/mm ² | 25N/mm² | |
| Frost Resist | | N/A | Not suitable | |
| Chemical Ro EN ISO 1054 | | Min Class B | Class A-B (better) | |
| Stain Resist EN ISO 1054 | | Min Class 3 | Class 3 (better) | |
| Fire Rating | | | Class A I Non Combustible | |
| kg Weight/m ² Thickness: 6 | 5mm | | 11.50kg | |

Available Sizes 200x100x6.5mm 150x150x6.5mm 200x200x6.5mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (30/04/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.



