## **NEPTUNITE PRODUCT DATA SHEET**



## **Available Sizes**

900x900x9.5mm 600x600x7.8mm 1200x600x8.8mm

## Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

## Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Ø Recycled Content	Up to 30%	
Range	Neptunite	
Category	Stone, Floor Tiles	
Collection	Absolute Collection	
Short Code	NPT01N	
Colour	lvory	
Finish	Natural	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
ight Reflectance Value	60.00	
CSV	V2	
PTV (96)	Wet 25-35 Dry 36+	
PTV (55)	-	
R Value	10	
Wet Ramp	-	
PEI	IV	
Traffic	Commercial	

Physi	Physical Properties				
Test /	Standard	Requirement	Test Result		
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass		
<b>→</b>	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass		
-]+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass		
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass		
$\begin{array}{ c c }\hline \downarrow \\\hline \uparrow \uparrow \uparrow \\\hline \end{array}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass		
	Water Absorption EN ISO 10545-3	≤0.5%	Pass		
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass		
	Thermal Shock EN ISO 10545-9	Pass	Pass		
<u>*</u>	Frost Resistance EN ISO 10545-12	Resistant	Resistant		
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A		
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 4		
~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~	UV Colour Resistance		Unaffected by light		
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible		
kg	Weight/m² Thickness: 7.8mm Thickness: 8.8mm Thickness: 9.5mm		19.05kg 24.31kg 24.31kg		

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (09/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5 JZ. Registered in England No. 156/04/37 @ 2025 Express Tiles (M. Lighter recovered).

