NEPTUNITE PRODUCT DATA SHEET



Available Sizes

900x900x9.5mm 1200x600x8.8mm 600x600x7.8mm 600x300x7.8mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Ø Recycled Content	Up to 30%	
Range	Neptunite	
Category	Stone, Floor Tiles	
Collection	Absolute Collection	
Short Code	NPT02L	
Colour	Silver	
Finish	Lapato	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	31.00	
CSV	V2	
PTV (4S)	Wet 0-24 Dry 36+	
PTV (TRL)	-	
R Value	-	
Wet Ramp	-	
PEI	III	
Traffic	Light Commercial	

Physical Properties				
Test / Standard		Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
→	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass	
-]+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
$\boxed{ \begin{array}{c} \downarrow \\ \uparrow \uparrow \uparrow \end{array} }$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
	Water Absorption EN ISO 10545-3	≤0.5%	Pass	
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass	
	Thermal Shock EN ISO 10545-9	Pass	Pass	
※	Frost Resistance EN ISO 10545-12	Resistant	Resistant	
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A	
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 4	
~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~	UV Colour Resistance		Unaffected by light	
	<b>Fire Rating</b> Not Applicable	N/A	Class A I FL Non Combustible	
kg	Weight/m ² Thickness: 7.8mm Thickness: 8.8mm Thickness: 9.5mm		19.05kg 24.31kg 24.31kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/2021). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road. Wilmslow. Cheshire, SK9 IBU. Registed in England No, 366694. Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks of H&R.

