NEPTUNITE PRODUCT DATA SHEET



	Short Code	NPT05L
	Colour	Steel
	Finish	Lapato
	Wall Suitability	Internal & External
	Floor Suitability	Internal Only
All all and a second	Wet Barefoot	-
	Material	Glazed Porcelain
00x600x7.8mm 200x600x8.8mm 00x300x7.8mm 00x900x9.5mm	Classificiation	Bla
	Light Reflectance Value	10.00
	CSV	V2
	PTV (4S)	Wet 0-24 Dry 36+
	PTV (TRL)	-
	R Value	-
)43 379	Wet Ramp	-
nson-tiles.com	PEI	ш
	Traffic	Light Commercial
524 577 379		
@johnson-tiles.com		

 \mathcal{O} Recycled Content

Range

Category Collection Up to 30%

Neptunite

Stone, Floor Tiles

Absolute Collection

Test / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
	±5%≤ ± 0.5mm	Pass
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
Water Absorption EN ISO 10545-3	≤0.5%	Pass
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Class A
Stain Resistance EN ISO 10545-14	Min Class 3	Class 4
UV Colour Resistance		Unaffected by light
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg Weight/m ² Thickness: 7.8mm Thickness: 8.8mm		19.05kg 24.31kg
Thickness: 9.5mm		24.31kg

Fax: +44 (0) 1782

Email: techadvice@jo

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a line bilip potential. 25 - 35 significant reduction and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/2021). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshire, SK91BU, Registed in England No. 566694. Johnson Tiles, Johnson Albute and Material Lab are registered trademarks and together with Kerastar and product name. Johnson Tiles Limited and licensed to Norcros Group (Holdings) Limited trading as Johnson Tiles. © 2021 Johnson Tiles. All rights reserved.

