NEPTUNITE PRODUCT DATA SHEET



	Category	Stone, Floor Tiles
	Collection	Absolute Collection
	Short Code	NPT05N
	Colour	Steel
	Finish	Natural
	Wall Suitability	Internal & External
	Floor Suitability	Internal Only
	Wet Barefoot	-
lable Sizes	Material	Glazed Porcelain
200x600x8.8mm 00x900x9.5mm 00x600x7.8mm	Classificiation	Bla
	Light Reflectance Value	10.00
	CSV	V2
	PTV (96)	Wet 25-35 Dry 36+
	PTV (55)	-
ples Service	R Value	10
+44 (0)1782 524 043 +44 (0)1782 577 379	WetRamp	-
l: samples@johnson-tiles.com	PEI	ш
nical Helpline 44 (0)1782 524 111	Traffic	Light Commercial
+44 (0) I 782 577 379 l: techadvice@johnson-tiles.com		

Physical Properties		
Test / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
→ Thickness ← EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
→ Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
Water Absorption EN ISO 10545-3	≤0.5%	Pass
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Class A
Stain Resistance EN ISO 10545-14	Min Class 3	Class 4
UV Colour Resistance		Unaffected by light
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg Weight/m ² Thickness: 7.8mm		19.05kg
Thickness: 8.8mm Thickness: 9.5mm		24.31kg 24.31kg

Sample

Technic

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (01/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2025 Johnson Tiles. All rights reserved.

 \mathcal{O} Recycled Content

Range

Up to 30%

Neptunite

JOHNSON _____TILES