## **NEWARK PRODUCT DATA SHEET**



Newark Range Category Stone, Structure Collection Absolute Collection Short Code NEW02D Colour Ivory Finish Matt - Rhombus Structure Wall Suitability Internal Only Floor Suitability -Wet Barefoot -Material Glazed Ceramic Classificiation BIII Light Reflectance Value 54.00

V2

Up to 40%

Physical Properties Test / Standard

 $\varnothing$  Recycled Content

	lest/	Standard	Requirement	lest Result
-		Length/Width EN ISO 10545-2	±0.5%≤ ± 2mm	Pass
-	$\rightarrow ]] \diamond$	Thickness EN ISO 10545-2	±10%≤±0.5mm	Pass
-	+	Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	Pass
-	-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	${\rightarrow} \boxed[\uparrow \uparrow$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
-		Water Absorption EN ISO 10545-3	10% to 20%	Pass
-		Modulus of Rupture EN ISO 10545-4	Ave 15N/mm <sup>2</sup>	Pass
-		Thermal Shock EN ISO 10545-9	Pass	Pass
-	*	<b>Frost Resistance</b> Not Applicable	N/A	Not suitable
-	ð	Chemical Resistance EN ISO 10545-13	Min Class B	Pass
-		<b>Stain Resistance</b> EN ISO 10545-14	Min Class 3	Pass
-		UV Colour Resistance		Unaffected by light
-		Fire Rating		Class A1 Non Combustible
-	kg	Weight/m <sup>2</sup> Thickness 8.7mm		16.74-
		Thickness 10.8mm		16.3kg 20.38kg
		1110011255 10.011111		20.30Kg

Requirement

## Available Sizes

## Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 = 24 represents a high slip potential, 25 = 53 signifies a moderate slip potential and 36r represents a low slip potential. All rigures are accurate at the time of this data sheets creation (27/05/2025). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. 0 2025 Johnson Tiles. All rights reserved.

CSV





Test Result