NORDIC WOOD PRODUCT DATA SHEET





Available Sizes

| ${oldsymbol{arOmega}}$ Recycled Content | Up to 40% | |
|---|---------------------|--|
| Range | Nordic Wood | |
| Category | Wood, Structure | |
| Collection | Absolute Collection | |
| Short Code | NOR02D | |
| Colour | Natural Oak | |
| Finish | Natural - Panelling | |
| Wall Suitability | Internal Only | |
| Floor Suitability | - | |
| Wet Barefoot | - | |
| Material | Glazed Ceramic | |
| Classificiation | BIII | |
| Light Reflectance Value | 19.00 | |
| CSV | V3 | |

Samples Service

Tel: +44 (0) | 782 524 043 Fax: +44 (0) | 782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

| Physical Properties | | | |
|---|---|-----------------|------------------------------|
| Test / Standard Requirement Test Result | | | Test Result |
| | Length/Width EN ISO 10545-2 | ±0.5%≤ ± 2mm | Pass |
| $\boxed{\qquad}$ | Thickness EN ISO 10545-2 | ±10%≤±0.5mm | Pass |
| -]+ | Straightness of Sides EN ISO 10545-2 | ±0.3% ≤ ± 1.5mm | Pass |
| | Rectangularity EN ISO 10545-2 | ±0.5% ≤ ± 2mm | Pass |
| $ \\ \boxed{ \uparrow \uparrow }$ | Surface Flatness EN ISO 10545-2 | ±0.5% ≤ ± 2mm | Pass |
| | Water Absorption EN ISO 10545-3 | 10% to 20% | > 10% |
| | Modulus of Rupture EN ISO 10545-4 | Ave I5N/mm² | Pass |
| | Thermal Shock EN ISO 10545-9 | Pass | Pass |
| * | Frost Resistance Not Applicable | N/A | Not suitable |
| | Chemical Resistance EN ISO 10545-13 | Min Class B | Class B |
| | Stain Resistance EN ISO 10545-14 | Min Class 3 | Pass |
| | UV Colour Resistance | | Unaffected by light |
| | Fire Rating | | Class A I Non Combustible |
| kg | Weight/m² Thickness 8.2mm | | 14.59kg |



