ORBY PRODUCT DATA SHEET



${\cal O}$ Recycled Content	Up to 10%	
Range	Огby	
Category	Stone, Speckle, Floor Tiles	
	PTV 36+ Tiles	
Collection	Select Collection	
Short Code	ORB02N	
Colour	Grey	
Finish	Natural	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	50.00	
CSV	V4	
PTV (4S)	Wet 36+ Dry 36+	
PTV (TRL)	-	
R Value	11	
Wet Ramp	В	
PEI	III	
Traffic	Light Commercial	

Physical Properties				
Test /	Standard	Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
$\rightarrow]] \leftrightarrow$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass	
+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
$\stackrel{\mathbf{h}}{=} \stackrel{\mathbf{h}}{=} \stackrel{\mathbf{h}}{=$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
	Water Absorption EN ISO 10545-3	≤0.5%	Pass	
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass	
The second secon	Thermal Shock EN ISO 10545-9	Pass	Pass	
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant	
ð	Chemical Resistance EN ISO 10545-13	Min Class B	Pass	
	Stain Resistance EN ISO 10545-14	Min Class 3	Pass	
	UV Colour Resistance		Unaffected by light	
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg	Weight/m ² Thickness: 7.2mm		15.8kg	

Samples Service

Available Sizes 330x330x7.2mm

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a lips flip potential. 25 - 35 significant reduction in and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/2021). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshire, SK9 IBU. Registed in England ho. 566694. Johnson Tiles. Johnson Tiles. Englisted and together with Kerastar and product names are the trademarks of H&R Johnson Tiles. Emitted and licensed to Norcros Group (Holdings) Limited trading as Johnson Tiles. © 2021 Johnson Tiles. All rights reserved.

